

## Colors

More colors available, color may vary from sample  
Call us about special orders, Color matching, and pre-fabricated products



## Sinks



## Specification

ITEM	NOMINAL VALUE	TEST METHOD
Specific Gravity	1.75g/cm <sup>3</sup>	ASTM-D-729A
Water Absorption	0.03%	ASTM-D-570
Hardness(Barcol)	56	ASTM-D-2583
Tensile Strength	5537psi	ASTM-D-638
Flexural Strength	8580psi	ASTM-D-790
Elongation At Yield	0.50%	ASTM-D-638
Glossiness	5-75	ANSI Z-124
Wear And Cleanability	pass	ANSI Z-124
Point Impact	no cracks	ANSI Z-124
Colorfastness	pass (200 hour)	ANSI Z-124
High Temperature Resistance	pass (180°C 20min)	ANSI Z-124
Stain Resistance	stain resistance rating: 30	ANSI Z-124
Chemical Resistance	pass	ANSI Z-124
Skillet Drop Test	pass	ANSI Z-124
Load Test	no cracks.The residual deflection is 0.2mm after removal of the load	ANSI Z-124
Water Resistance	pass	ANSI Z-124
Ignition Test	burning ceases within 5 seconds	ANSI Z-124

U.S.A:

**Worldwide Surface,Inc**

TEL:(945)438 3762

E-mail:WWSINC1@cs.com